


BLACK PEN-SPP

TOP DYEING - 3%



SPLIT - 3%



PENETRATION



60° Solubility	Penetration	Light	F A S T N E S S					
			PERSPIRATION			WASHING		
			CS	SC	SW	CS	SC	SW
60	6-7	2-3	3-4	2-3	4	2-3	2-3	3

SCALE - 1 TO 5

CS - COTTON + SILK

SC - SPUN DIACETATE

SW - SPUN WOOL